

AE154 POLY-ALKYD BRUSH TOPCOAT

Compilation date: 23/06/2015

Revision No: 1

DESCRIPTION	Single component air drying brush topcoat based on polyurethane resins
USES & BENEFITS	<ul style="list-style-type: none"> • Topcoat for brush application to internal or external wood & metal • Good coverage & gloss retention • Available in a wide range of colours includes metallic's
PHYSICAL PROPERTIES*	VOC Content : 410g/Ltr Solids % by Weight : 59 Flash Point : 36°C Mixing Ratio : N/A
FINISH	Gloss Semi-Gloss Eggshell Matt
COLOUR	Unlimited
COVERAGE	Up to 14m ² /Ltr
PREPARATION	Apply over a clean, dry and undamaged compatible primer
APPLICATION	Brush / roller : Unthinned Conventional spray : Thin <10% Ambient temperature : 5-30°C Surface temperature : >3°C above the dew point Clean equipment with STD Thinner
DRYING TIMES	At 20°C Touch dry : 2-4 Hours Hard dry : 24-48 Hours Recoat : After 16 hours
THINNER	SV104
STORAGE	Keep away from food and drink. Store in original container securely closed and at room temperature (For full text refer to health & safety data sheet)
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.