

AE155 ALKYD PRIMER / TOPCOAT

 Compilation date: 24/06/2015
 Revision No: 2

DESCRIPTION	Single component self-priming topcoat based on modified alkyd resin
USES & BENEFITS	<ul style="list-style-type: none"> • For refurbishment of steel skips / containers, plant & machinery • Anti-corrosive – can be applied direct to bare steel • High build & fast drying • Available in a wide range of colours
PHYSICAL PROPERTIES*	VOC Content : 410g/Ltr Solids Content % by Weight : 62.7 Flash Point : 26 °C Mixing Ratio : N/A
FINISH	Gloss Semi-Gloss Eggshell Matt
COLOUR	Unlimited
COVERAGE	Up to 9m ² /Ltr
PREPARATION	Substrate to be clean, dry and free from rust, grease and mill scale. Best results by blast cleaning
APPLICATION	Brush / Roller : Unthinned Airless Spray : Unthinned Conventional spray : Thin <15% Ambient temperature : 5-30°C Surface temperature : >3°C above the dew point Clean equipment with STD Thinner
DRYING TIMES	At 20°C Touch dry : 30 Minutes Hard dry : 16 Hours Recoat : Within 4 hours or after 16 hours
THINNER	SV100
STORAGE	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet)
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Minimum respiratory protection A1P2 carbon activated mask. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Unova Limited be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.

UNOVA PRODUCTS

| Bennet Road, Reading, Berks, RG2 0QX | T: 01753 584500 | F: 01753 584501 | E: sales@unovaproducts.com |