

AE252 – WB HIGH ADHESION FOR GLASS

Compilation date: 07/09/2015
Revision No: 1

DESCRIPTION	Single component waterborne environmentally friendly coating
USES & BENEFITS	<ul style="list-style-type: none"> • Primer / finish coat with excellent direct adhesion to a wide range of substrates including powder coated surfaces & glass • Excellent hardness & abrasion resistance • Low odour & fast drying
PHYSICAL PROPERTIES*	VOC Content : 680g/Ltr Solids % by Weight : 32 Flash Point : n/a Mixing Ratio : (optional) for extra hardness add 2% HA501
FINISH	Semi-Gloss Eggshell Matt
COLOUR	Unlimited
COVERAGE	Up to 8-10m ² /Ltr
PREPARATION	Substrate to be lightly abraded, clean & dry
APPLICATION	Conventional Spray : Thin <5% Pressure Fed : Thin <5% Ambient temperature : 15-30°C Surface temperature : >3°C above the dew point Clean equipment with Water or PT212
DRYING TIMES	At 20°C (RH<65% with good air movement) Touch dry : 30 minutes Hard dry : 4 hours
THINNER	SV109
STORAGE	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet). PROTECT FROM FREEZING.
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.