

FP171 – FLOORCOAT NON SLIP

DESCRIPTION	Single component non slip floor paint based on polyurethane resin
USES & BENEFITS	<ul style="list-style-type: none"> * For fast transformation of concrete floors subject to light traffic * Seals & colours in 1 or 2 coats * Easy to apply & fast drying * Tough oil resistant finish
PHYSICAL PROPERTIES*	VOC Content : 570g/Ltr Solids % by Weight : 43 Flash Point : >32°C Mixing Ratio : n/a
FINISH	Gloss
COLOUR	Limited range
COVERAGE	Up to 10m ² /Ltr
PREPARATION	Correct and thorough surface preparation is essential to the success of any floor coating project. As the preparation procedure will vary according to the condition of the concrete we would recommend that you contact our technical department for specific advice
APPLICATION	Apply by brush or roller – unthinned For initial sealer coat on bare concrete thin 20% Ambient temperature 5-30°C Surface at least 3°C above the dew point Clean equipment with STD Thinner
DRYING TIMES	At 20°C Touch dry – 2 hours Hard dry – 24-48 hours Recoat – after 16 hours & within 7 days. After 7 days abrade surface to provide key
THINNER	SV104
STORAGE	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet)
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.

THAMES COATINGS