

FP175 – FLOORCOAT

Compilation date: 18/08/2017

Revision No: 1

DESCRIPTION	Single component floor paint based on polyurethane resin	
USES & BENEFITS	<ul style="list-style-type: none"> • For fast transformation of concrete floors subject to light traffic • Seals & colours in 1 or 2 coats • Easy to apply & fast drying onto concrete, wood and metal • Tough oil resistant finish • Also available in a non-slip version 	
PHYSICAL PROPERTIES*	VOC Content	: 570g/Ltr
	Solids % by Weight	: 43
	Flash Point	: <32°C
	Mixing Ratio	: n/a
FINISH	Gloss	
COLOUR	Limited Range	
COVERAGE	Up to 10m ² /Ltr	
PREPARATION	Correct and thorough surface preparation is essential to the success of any floor coating project. As the preparation procedure will vary according to the condition of the substrate we would recommend that you contact our technical department for specific advice.	
APPLICATION	Brush	: Unthinned
	Roller	: Unthinned
	For sealer coat on bare concrete	: Thin 20%
	Ambient temperature	: 5-30 °C
	Surface temperature	: >3°C above the dew point
	Clean equipment with STD Thinner	
DRYING TIMES	At 20°C	
	Touch dry	: 2 Hours
	Hard Dry	: 24-48 Hours
	Recoat	: After 16 hours & within 7 Days (after 7 Days abrade surface to provide a key)
THINNER	SV104	
STORAGE	Keep in original container securely sealed at minimum 15°C. Containers that have been stored at lower temperatures will need to be pre warmed prior to use.	
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.	
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.	

For paint system recommendations specific to your job requirements please contact our technical department.