

## FP176 – FLOORCOAT SF AS

<b>DESCRIPTION</b>	Two component solvent free epoxy floor paint with anti-static properties
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>* High build dissipative coating to prevent the build-up of static charge</li> <li>* Extremely hard &amp; chemical resistant</li> <li>* Low odour &amp; VOC</li> <li>* Seamless easy-clean hygienic finish</li> </ul>
<b>PHYSICAL PROPERTIES*</b>	VOC Content : 20g/Ltr Solids % by Weight : 98 Flash Point : >100 °C Mixing Ratio : As supplied Surface Resistance : <10 <sup>8</sup> Ohms
<b>FINISH</b>	Gloss
<b>COLOUR</b>	Red or Grey
<b>COVERAGE</b>	Approx 4-5m <sup>2</sup> /Ltr Depending on application thickness & surface profile
<b>PREPARATION</b>	Correct and thorough surface preparation is essential to the success of any floor coating project. As the preparation procedure will vary according to the condition of the concrete we would recommend that you contact our technical department for specific advice.
<b>APPLICATION</b>	Must be applied over AS Primer Apply mixed material with brush / roller Ambient temperature 5-30°C Surface at least 3°C above the dew point Clean equipment with STD Thinner
<b>DRYING TIMES</b>	At 20°C Pot life – 40 mins Touch dry – 4 hours Overcoat – after 14 hours and within 48 hours Through dry – 24 hours Full cure – 7 days
<b>THINNER</b>	-
<b>STORAGE</b>	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet)
<b>HEALTH &amp; SAFETY</b>	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

*For paint system recommendations specific to your job requirements please contact our technical department.*

### THAMES COATINGS