

FP292 – NEVASLIP

DESCRIPTION	Single component vinyl coating containing non slip particles
USES & BENEFITS	<ul style="list-style-type: none"> * Slip resistant finish for use in hazardous areas * Will adhere direct to a wide range of substrates * Good resistance to acids, alkalis, oils & detergents * Quick and easy one coat application
PHYSICAL PROPERTIES*	VOC Content : 395g/Ltr Solids % by Weight : 78.8 Flash Point : 4 °C Mixing Ratio : n/a
FINISH	Flat
COLOUR	Any colour
COVERAGE	Approx 1m ² /Ltr
PREPARATION	Ensure surface is sound, dry and free from contamination such as oil, grease and loose material. Abrade surface to provide key. If surface has already been painted trial a small amount of FP292 Nevaslip to ensure coating compatibility
APPLICATION	Spread the material evenly using a non spark tool e.g. squeegee and press down sufficiently hard to ensure wet film is no thicker than one grit particle Ambient temperature 5-30°C Surface at least 3°C above the dew point Clean equipment with STD Thinner
DRYING TIMES	At 20°C Touch dry – 2 hours Light traffic – overnight Full cure – 7 days
THINNER	SV203
STORAGE	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet)
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.

THAMES COATINGS

| Sutton Lane, Langley, SL3 8AR | T: 01753 584500 | F: 01753 584501 | E: office@thamescoatings.co.uk |