

### PR132 – EASICOTE UNDERCOAT

Compilation date: 25/09/2015

Revision No: 1

<b>DESCRIPTION</b>	Single component primer based on Acrylic resins
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>• Provides a tough, durable, flexible film</li> <li>• Exceptional weathering properties</li> <li>• Can be applied over most previously painted surfaces without reaction</li> <li>• Fast drying</li> </ul>
<b>PHYSICAL PROPERTIES*</b>	VOC Content : 500g/Ltr Solids % by Weight : 55 Flash Point : 25°C Mixing Ratio : n/a
<b>FINISH</b>	Low Sheen
<b>COLOUR</b>	Limited
<b>COVERAGE</b>	Approximately 8-10m <sup>2</sup> /Ltr
<b>PREPARATION</b>	Surfaces must be clean, dry and free from dust, grease, oil, mill scale etc.
<b>APPLICATION</b>	Brush / Roller : Unthinned Conventional Spray : Thin <10% Ambient temperature : 5-30°C Surface temperature : >3°C above the dew point Clean equipment with STD Thinner
<b>DRYING TIMES</b>	At 20°C Touch dry : 20 minutes
<b>THINNER</b>	SV102
<b>STORAGE</b>	Keep away from food and drink. Store in original container securely closed and at room temperature (For full text refer to health & safety data sheet)
<b>HEALTH &amp; SAFETY</b>	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

*For paint system recommendations specific to your job requirements please contact our technical department.*