

PR229 – WATERBORNE PRIMER

DESCRIPTION	Single component environmentally friendly primer
USES & BENEFITS	<ul style="list-style-type: none"> * Fast dry primer specifically for MDF flat parts & profiles * Excellent filling properties * High pigment & solid content * Uniform basecoat
PHYSICAL PROPERTIES*	VOC Content : 53g/Ltr Solids % by Weight : 61 Flash Point : n/a Mixing Ratio : n/a
FINISH	Flat
COLOUR	White or Grey
COVERAGE	8 – 10 m ² /Ltr
PREPARATION	Apply direct to clean, dry, dust free MDF
APPLICATION	Conventional, Airmix or Airless spray – thin up to 10% Ambient temperature 15-30°C Surface at least 3°C above the dew point Clean equipment with Water or PT212
DRYING TIMES	At 20°C, RH < 65%, Good air movement Touch dry – 20 minutes Recoat up to 3 coats @ 1 hour intervals Overcoat – After 4 hours
THINNER	Water
STORAGE	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet) PROTECT FROM FREEZING.
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.

THAMES COATINGS