

PRODUCT DATA SHEET

PR232 - PRECAT PRIMER

DESCRIPTION	Single component precatalyzed pigmented primer
USES & BENEFITS	General purpose high build basecoat for wood including MDF
OSES & BENEFITS	* Fast drying
	* Excellent sandability
	* Can be force dried
PHYSICAL PROPERTIES*	
PHISICAL PROPERTIES	3.13
	Solids % by Weight : 52
	Flash Point : <21 ℃
	Mixing Ratio : n/a
FINISH	Flat
COLOUR	White or grey
COVERAGE	6-9m²/Ltr
PREPARATION	Substrate to be thoroughly abraded and free from surface contamination and dust
APPLICATION	Conventional & pressure fed systems – Thin 15%
	Ambient temperature 18-25°C
	Clean equipment with STD Thinner
DRYING TIMES	At 20°C Touch dry – 30 minutes Recoat – up to 3 coats at 1-3 hour intervals
	Force dry – 40 minutes @ 50 °C after 20 minutes flash off
	Topcoat application – After force dry or 16 hours
THINNER	SV107 Thinner
STORAGE	Keep in original container securely sealed at minimum 15 ℃. Containers that have
	been stored at lower temperatures will need to be pre warmed prior to use.
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.

THAMES COATINGS