

# PT115 – T-WASH MORDENT SOLUTION

Compilation date: 09/09/2015

Revision No: 1

<b>DESCRIPTION</b>	Blue solution containing a small proportion of phosphoric acid
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>• Pre-treatment solution for galvanized substrates</li> <li>• Neutralises the surface and provides a key for subsequent coatings</li> <li>• Effectiveness off treatment is confirmed by surface colour change to black</li> </ul>
<b>PHYSICAL PROPERTIES*</b>	VOC Content : 780g/Ltr Flash Point : 12°C Mixing Ratio : n/a
<b>COVERAGE</b>	Up to 15m <sup>2</sup> /Ltr
<b>PREPARATION</b>	Surface to be clean, dry and free from traces of grease and oil
<b>APPLICATION</b>	Brush or swab : Unthinned* Ambient temperature : 5-30°C Surface temperature : >3°C above the dew point *Further treatment will be required on areas that have not turned black. A white deposit indicates excess which should be removed with a lint free cloth. After successful conversion rinse all areas down with fresh clean water. Clean equipment with STD Thinner
<b>DRYING TIMES</b>	Dependent on temperature, air movement & relative humidity Allow to fully dry before overcoating with subsequent paint systems
<b>STORAGE</b>	Store in original container securely closed and in a cool, dry, well ventilated place away from sources of ignition (For full text refer to health & safety data sheet)
<b>HEALTH &amp; SAFETY</b>	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages.

*For paint system recommendations specific to your job requirements please contact our technical department.*