

## PRODUCT DATA SHEET

## PT215 CONCRETE FLOOR ETCH SOLUTION

Compilation date: 30/06/2015

Revision No: 1

| DESCRIPTION     | A pre-treatment for concrete surfaces which improves adhesion prior to painting with the  |
|-----------------|---|
|                 | appropriate floor coating.  |
| USES & BENEFITS | Removes the laitance (weak top layer of concrete)   |
|                 | Improves adhesion of floor coatings.  |
| COVERAGE        | Up to 4m²/Ltr (Just enough is NOT enough)   |
| PREPARATION     | Concrete surfaces should be clean and degreased before application using detergent wash or steam cleaning and rinsed with fresh water before application.   |
| APPLICATION     | Apply evenly by soft brush/broom and allow time to react (around 15 Minutes). Two or more applications may be required depending on the amount of laitance present. After the reaction has taken place, the surface should be rinsed with water to remove loose particles and all soluble materials, until the washings are acid free, and allowed to dry before priming.   |
| STORAGE         | Keep away from food and drink. Store in original container securely closed and at room temperature (For full text refer to health & safety data sheet)  |
| HEALTH & SAFETY | Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately. |
| DISCLAIMER      | The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages.   |

For paint system recommendations specific to your job requirements please contact our technical department.