

## SL192 – ROAD LINE PAINT

<b>DESCRIPTION</b>	Single component rapid dry line marker
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>* Line mark product for roads, runways, car parks &amp; sports facilities</li> <li>* Can be applied direct to concrete, asphalt, block &amp; brick surfaces</li> <li>* Good colour retention</li> <li>* Abrasion resistant</li> </ul>
<b>PHYSICAL PROPERTIES*</b>	VOC Content : 620g/Ltr Solids % by Weight : 44.6 Flash Point : 26°C Mixing Ratio : n/a
<b>FINISH</b>	Flat
<b>COLOUR</b>	Yellow, white, red & black
<b>COVERAGE</b>	2-3m <sup>2</sup> /Ltr depending on surface profile
<b>PREPARATION</b>	Ensure surface is dry and free from dust and contamination
<b>APPLICATION</b>	Brush, roller or airless spray – use unthinned Ambient temperature 5-30°C Surface at least 3°C above the dew point Clean equipment with STD Thinner
<b>DRYING TIMES</b>	At 20°C Touch dry 5-10 minutes Hard dry 12-24 hours
<b>THINNER</b>	SV100 Thinner
<b>STORAGE</b>	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet)
<b>HEALTH &amp; SAFETY</b>	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

*For paint system recommendations specific to your job requirements please contact our technical department.*

### THAMES COATINGS

| Sutton Lane, Langley, SL3 8AR | T: 01753 584500 | F: 01753 584501 | E: office@thamescoatings.co.uk |