

## SL194 – BLACK BITUMEN PAINT

<b>DESCRIPTION</b>	Single component high build solvent borne bituminous black paint
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>* Waterproof coating for steel and concrete.</li> <li>* Thixotropic for high build application</li> <li>* Tough, flexible film</li> <li>* Fast Drying for quick handling times</li> </ul>
<b>PHYSICAL PROPERTIES*</b>	VOC Content : 440g/Ltr Solids % by Weight : Flash Point : 34°C Mixing Ratio : n/a
<b>FINISH</b>	Flat
<b>COLOUR</b>	Black
<b>COVERAGE</b>	Approx 4.6m <sup>2</sup> /Ltr @ 100 microns dft
<b>PREPARATION</b>	All surfaces to be clean, dry and free from loose or flaking material, rust and grease. Areas of rust should be thoroughly wire brushed and treated with RC140. For maximum protection blast clean steel to SA2.5.
<b>APPLICATION</b>	Brush or Roller Apply unthinned. Airless Spray – 15-19 thou tip @ 2000-2400 psi Ambient temperature 5-30°C Surface at least 3°C above the dew point Clean equipment with STD Thinner
<b>DRYING TIMES</b>	At 15°C Touch dry: 45 mins      Hard dry: 3 hours      Overcoat: 24 hours
<b>THINNER</b>	SV104
<b>STORAGE</b>	Containers must be kept sealed and stored undercover away from sources of heat and ignition.
	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

*For paint system recommendations specific to your job requirements please contact our technical department.*

### THAMES COATINGS

| Sutton Lane, Langley, SL3 8AR | T: 01753 584500 | F: 01753 584501 | E: office@thamescoatings.co.uk |