

## TC268 – 2PK ACID CAT LACQUER

<b>DESCRIPTION</b>	Two component ureic lacquer available in either a pigmented or clear finish	
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>* Wood finish for domestic / commercial fitted interiors</li> <li>* Fast dry</li> <li>* More durable than precat</li> </ul>	
<b>PHYSICAL PROPERTIES*</b>	VOC Content	: 540g/Ltr
	Solids % by Weight	: 44
	Flash Point	: <21 °C
	Mixing Ratio	: Mix 10:1 with HA403
<b>FINISH</b>	% Gloss : 10, 25, 40	
<b>COLOUR</b>	Clear, solid colour or metallic	
<b>COVERAGE</b>	Approx 10m <sup>2</sup> /Ltr	
<b>PREPARATION</b>	Clear version can be applied coat on coat onto abraded dust free substrate Pigmented version to be applied over a compatible sealer coat	
<b>APPLICATION</b>	Conventional & pressure fed spray systems Ambient temperature 18-25°C Clean equipment with STD Thinner	
<b>DRYING TIMES</b>	At 20°C Touch dry – 1 hour                      Pot life – 24 hours Hard dry – 6 hours	
<b>THINNER</b>	SV108	
<b>STORAGE</b>	Store in original container securely closed at minimum 15°C. Containers that have been stored at lower temperatures will need to be pre warmed prior to use. (For full text refer to health & safety data sheet)	
<b>HEALTH &amp; SAFETY</b>	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.	
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.	

*For paint system recommendations specific to your job requirements please contact our technical department.*

### THAMES COATINGS

| Sutton Lane, Langley, SL3 8AR | T: 01753 584500 | F: 01753 584501 | E: office@thamescoatings.co.uk |