

TC285 – TARMACADAM COATING

DESCRIPTION	Single component tarmac coating based on modified chlorinated rubber
USES & BENEFITS	<ul style="list-style-type: none"> * For tarmacadam surface rejuvenation and area identification * Obliterates old lines and stains * Rapid dry * Non slip version also available
PHYSICAL PROPERTIES*	VOC Content : 610g/Ltr Solids % by Weight : 45 Flash Point : 26°C Mixing Ratio : n/a
FINISH	Flat
COLOUR	Limited range
COVERAGE	Up to 5m ² /Ltr depending on surface profile
PREPARATION	Remove all loose material back to a firm edge and ensure surface is clean, dry and free from contamination
APPLICATION	Brush, roller or airless spray – material supplied ready for use Ambient temperature 5-30°C Surface at least 3°C above the dew point Clean equipment with STD Thinner
DRYING TIMES	At 20°C Touch dry – 15 minutes Overcoat – After 1 hour Hard dry – 24 hours
THINNER	SV100
STORAGE	Store in original container securely closed and in a dry, well ventilated area away from sources of heat and ignition. (For full text refer to health & safety data sheet)
HEALTH & SAFETY	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
DISCLAIMER	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

For paint system recommendations specific to your job requirements please contact our technical department.

THAMES COATINGS

| Sutton Lane, Langley, SL3 8AR | T: 01753 584500 | F: 01753 584501 | E: office@thamescoatings.co.uk |