

# U-POL®

## BARCOAT

### Quick Drying Isolator

<b>Description</b>	<b>BARCOAT</b> is a quick drying yellow oxide isolator. It is designed to prevent lifting and bleeding of existing paint film sensitive to solvent attack when overcoated with cellulose or paint containing strong solvents.
<b>Surface preparation and instructions for use</b>	Thoroughly clean and de-wax the old paint surface with a spirit wipe or suitable solvent. Wet sand with P400 paper, re-clean and dry thoroughly. For metal use P180 paper.
<b>Health and Safety Statement</b>	FOR PROFESSIONAL USE ONLY. Read full instructions before use. IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at <a href="http://WWW.U-POL.COM">WWW.U-POL.COM</a> . U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.
<b>Thinners</b>	<b>BARCOAT</b> is supplied ready for use, no thinners are required. Use alcohol based gun wash to clean equipment after use.
<b>Build and Pressure</b>	One light even coat of <b>BARCOAT</b> will give a build of approximately 15-25 microns. A pressure of 3.5-4.0 BAR is required at the gun.
<b>Drying Time</b>	Approximately 1 hour at normal shop temperatures. Drying time is dependent on film thickness, humidity and temperature.
<b>Over painting</b>	<b>BARCOAT</b> should be overcoated with primer/surfacers. <b>BARCOAT</b> should <b>not</b> be sanded before application of further coats of paint.
<b>Product Code</b>	BAR/1 - 1L tin.
<b>VOC Information</b>	The EU limit for this product (product category: IIBe) in ready to use form is 840g/litre. The VOC content of this product in ready to use form is 535g/litre

U-POL, 1 TOTTERIDGE LANE, WHETSTONE, LONDON, N20 0EY, UK  
Home Sales T: +44(0)870 899 8200; F:+44(0)870 899 8211; E: [sales@u-pol.com](mailto:sales@u-pol.com);  
Export Sales T: +44(0)870 899 8200; F:+44(0)870 899 8299; E: [exportsales@u-pol.com](mailto:exportsales@u-pol.com);  
Technical T: +44(0)870 899 8310; F:+44(0)870 899 8351; E: [technicaldepartment@u-pol.com](mailto:technicaldepartment@u-pol.com);  
WEBSITE : [WWW.U-POL.COM](http://WWW.U-POL.COM)