

UC130 – SPRAY UNDERCOAT

Compilation date: 25/09/2015 Revision No: 1

PRODUCT

DATA

SHEET

| DESCRIPTION | Single component spray undercoat based on a modified alkyd resin | | | | |
|-----------------|---|--|----------------------|--------------------|------------|
| USES & BENEFITS | Intermediate coat for suitably primed steelwork High Build Excellent flow and opacity Can be overcoated with a wide range of single pack topcoats. | | | | |
| | | | Fast drying. | | |
| | | | PHYSICAL PROPERTIES* | VOC Content | : 450g/Ltr |
| | | | | Solids % by Weight | : 61 |
| | Flash Point | : 26°C | | | |
| Mixing Ratio | : n/a | | | | |
| FINISH | Flat | | | | |
| COLOUR | Limited | | | | |
| COVERAGE | Up to 10m ² /Ltr | | | | |
| PREPARATION | Suitably primed surface to be clean, dry and undamaged. | | | | |
| APPLICATION | Brush / Roller | : unthinned | | | |
| | Airless Spray | : unthinned | | | |
| | Conventional Spray | : 10-15% | | | |
| | Ambient temperature | : 5-30°C | | | |
| | Surface temperature | : >3°C above the dew point | | | |
| | Clean equipment with STD Thinner | | | | |
| DRYING TIMES | At 20°C | | | | |
| | Touch dry | : 15 minutes | | | |
| | Recoat | : Within 4 hours or after 16 hours.: 4 hours | | | |
| THINNER | SV100 | | | | |
| STORAGE | Keep away from food and drink. Store in original container securely closed and at | | | | |
| | room temperature (For full text refer to health & safety data sheet) | | | | |
| HEALTH & SAFETY | Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately. | | | | |
| DISCLAIMER | The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour. | | | | |

For paint system recommendations specific to your job requirements please contact our technical department.

THAMES COATINGS