

**UC131 – BRUSH UNDERCOAT**

Compilation date: 25/09/2015

Revision No: 1

<b>DESCRIPTION</b>	Single component brush undercoat based on a modified alkyd resin
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>• For use on suitably primed or suitably prepared previously painted surfaces</li> <li>• Excellent flow and opacity</li> <li>• Available in a range of colours</li> <li>• Quick drying</li> </ul>
<b>PHYSICAL PROPERTIES*</b>	VOC Content : 3606g/Ltr Solids % by Weight : 70 Flash Point : >36°C Mixing Ratio : n/a
<b>FINISH</b>	Flat
<b>COLOUR</b>	L:imited
<b>COVERAGE</b>	Up to 15m <sup>2</sup> /Ltr
<b>PREPARATION</b>	Substrate to be clean, dry and free from grease, rust and mill scale. Remove loose and flaking material back to a firm edge.
<b>APPLICATION</b>	Brush : Unthinned Roller : Unthinned Ambient temperature : 5-30°C Surface temperature : >3°C above the dew point Clean equipment with SV104 or White spirit
<b>DRYING TIMES</b>	At 20°C Touch dry : 15-30 minutes Recoat : Overnight
<b>THINNER</b>	SV104
<b>STORAGE</b>	Keep away from food and drink. Store in original container securely closed and at room temperature (For full text refer to health & safety data sheet)
<b>HEALTH &amp; SAFETY</b>	Refer to Health & Safety Data Sheet before using this product. Please observe the precautionary notices displayed on the container. Spray application (if appropriate) should be done under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleaner, soap and water. Eyes should be well flushed with fresh clean water and medical attention sought immediately.
<b>DISCLAIMER</b>	The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. User will be deemed to have satisfied themselves independently as to the suitability of this product for their own particular purpose. In no event shall Thames Coatings be liable for consequential or incidental damages. * VOC and solids content may vary with colour.

*For paint system recommendations specific to your job requirements please contact our technical department.*